



貿晨科技有限公司
Morechange Technology CO., LTD.

腐蝕負極鋁箔

Etched Alum Cathode Foil

規格	材料純度	厚度	容量	抗拉		抗彎	CL-含量	CU ²⁺ 含量	可裁寬
		Thickness	Capacitance						
Specification	Foil Purity	Um	Uf/cm2	Tensile Strength		Bending Strength	CL- Residual	CU ²⁺ Residual	Cutting width
	%	±2	(+30% -10%)	N/cm	Kgf/cm	Counts/cm	mg/m2	mg/m2	mm
ECM-2021	≥98.4	22	100	15.6	1.6	65	≤1.0	≤5.0	≥6.0
ECM-3011	≥98.4	28	150	18.6	1.9	70	≤1.0	≤5.0	≥5.0
ECM-3021			200	17.6	1.8	70	≤1.0	≤5.0	≥6.0
ECM-4011	≥98.4	38	350	18.6	1.9	80	≤1.0	≤5.0	≥5.0
ECM-4021			400	18.6	1.9	80	≤1.0	≤5.0	≥5.0
ECM-4031			450	18.6	1.9	80	≤1.0	≤5.0	≥5.0
ECM-5011	≥98.4	42	350	21.5	2.2	90	≤1.0	≤5.0	≥3.5
ECM-5031			500	19.5	2.0	90	≤1.0	≤5.0	≥5.0
ECM-5013	≥98.4	48	350	22.5	2.3	100	≤1.0	≤5.0	≥2.2
ECM-5023			450	22.5	2.3	100	≤1.0	≤5.0	≥2.2
ECM-5033			500	22.5	2.3	100	≤1.0	≤5.0	≥2.2
ECM-5043			600	18.6	1.9	90	≤1.0	≤5.0	≥5.0
ECM-5021	≥99.4	46	450	18.6	1.9	90	≤1.0	≤5.0	≥5.0
ECM-2011	≥99.7	24	80	11.7	1.2	55	≤1.0	≤5.0	≥12
ECM-3021	≥99.7	30	160	15.7	1.5	65	≤1.0	≤5.0	≥8.0
ECM-5021	≥99.7	48	450	17.6	1.8	80	≤1.0	≤5.0	≥5.0